



**NOTES:**

1. PORTLAND CEMENT CONCRETE (P.C.C.) SHALL BE 4000 PSI MIN. COMPRESSIVE STRENGTH AT 28 DAYS. ALL CEMENT CONCRETE SHALL HAVE A COARSE AGGREGATE GRADATION CONFORMING TO SIZE No. 67. POLYPROPYLENE OR CELLULOSE FIBERS SHALL BE ADDED TO THE P.C.C. AT 1.5 LBS PER CUBIC YARD. MIX DESIGN SHALL CONFORM TO THE REQUIREMENTS OF SECTION 337.10 OF SSPWC. ALL MATERIALS SHALL CONFORM TO SSPWC.
2. AGGREGATE BASE MATERIAL UNDER AND BEHIND CURB AND GUTTER SHALL BE TYPE 2, CLASS B CRUSHED AGGREGATE BASE. ALL MATERIALS SHALL CONFORM TO SSPWC.
3. WEAKENED PLANE JOINTS SHALL MATCH THE SPACING OF ADJACENT SIDEWALK OR DRIVEWAY AND IN ACCORDANCE WITH SECTION 312 OF SSPWC.
4. SIDEWALK AND/OR DRIVEWAY SECTIONS MAY BE PLACED MONOLITHICALLY WITH POST CURB SECTIONS.



STANDARD DETAILS FOR PUBLIC WORKS CONSTRUCTION

**P.C.C. REINFORCED  
RETAINING CURB**

DRAWING No.

**R-111**

APPROVED BY: KK

DATE: 2/2026